

FPC12-40 FULBATERY

www.fulbat.com - 🙃 FULBAT




NON-SPILLABLE

FPC Series are deep cycle batteries specially designed for long duration cyclic applications, ie with use in charge and then intensive discharge. With advanced AGM valve regulated technology and oversized negative plates, the FPC Series ensure very good cyclic performance with greater depth of discharge for mobility-type applications such as medical, golf and also renewable energies storage. In harsh use conditions (high temperature, higher deep of discharge...), the Gel FPG range is recommended.


DIMENSIONS & WEIGHT

LENGHT	197±2mm
WIDTH	165±2mm
TOTAL HEIGHT	170±2mm
WEIGHT	14.2kg (tolerance ± 3%)





TERMINAL (MM)



SPECIFICATION								
Nominal voltage	12V (6 cells)							
Nominal capacity	40.8Ah (20hr)							
Cycle life	Up to 400 cycles at 80% DOD* (80% capacity - 20°C) Up to 500 cycles at 50% DOD* (80% capacity - 20°C)							
Internal resistance	Approx 9mΩ							
Terminal	TG							
Max. discharge current	456A (5 sec)							
Reference capacity	40.8Ah (20hr, 1.80V/cell, 25°C/77°F) 38.0Ah (10hr, 1.80V/cell, 25°C/77°F) 33.4Ah (5hr, 1.75V/cell, 25°C/77°F) 30.3Ah (3hr, 1.75V/cell, 25°C/77°F) 24.5Ah (1hr, 1.60V/cell, 25°C/77°F)							
Charge voltage Standby use voltage	13.5V ~ 13.8V 25°C/77°F Temperature compensation: -20mV/°C/Cell							
Cycle use voltage	14.4V ~ 15.0V 25°C/77°F Temperature compensation: -20mV/°C/Cell							
Operating temp. range	Discharge: -15°C ~ 50°C Charge: 0°C ~ 40°C Storage: -15°C ~ 40°C							
Nominal operating temp. range	25°C ± 3°C / 77°F ± 5°F							
Self discharge	Can be stored for up to 6 months at 25°C/77°F and then recharging is recommended. Monthly self-discharge ratio is less than 3% at 25°C/77°F							
Capacity affected by temp.	40°C/104°F 103% 25°C/77°F 100% 0°C/32°F 86%							
Container material	A.B.S. UL94-HB							
	*DDD = Depth of discharge							

APPLICATIONS



APPROVALS

ISO9001 - Quality management system ISO14001 - Environnmental management System Approved for transport by Air (IATA)



DATA SHEET

FULBAT FPC12-40 CYCLIC BATTER

www.fulbat.com - 🛛 FULBAT


CONSTANT CURRENT DISCHARGE (AMPERES) AT 25°C/77°F

F.V/Time	10min	15min	20min	30min	45min	1h	Zh	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	55.6	46.8	40.9	29.4	23.4	19.0	11.8	9.19	7.44	6.05	5.28	4.31	3.59	2.02
1.80V/cell	71.1	56.6	48.4	34.7	27.2	21.3	12.9	9.89	7.95	6.49	5.66	5.66	5.66	5.66
1.75V/cell	78.1	61.8	52.0	36.1	28.2	22.2	13.3	10.1	8.12	6.67	6.67	4.65	3.84	2.06
1.70V/cell	85.1	66.0	54.7	37.5	29.3	22.9	13.9	10.4	8.34	6.83	5.94	4.71	3.88	2.09
1.65V/cell	91.9	70.1	58.1	39.6	30.1	23.7	14.3	10.8	8.63	7.02	6.06	4.79	3.96	2.12
1.60V/cell	99.8	75.0	61.9	41.8	31.4	24.5	14.7	11.1	8.90	7.25	6.20	4.83	4.00	2.13


CONSTANT POWER DISCHARGE (WATTS/CELL) AT 25°C/77°F

F.V/Time	10min	15min	20min	30min	45min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	103.8	88.3	78.0	56.6	45.2	36.8	23.0	18.0	14.6	11.9	10.42	8.52	7.11	4.04
1.80V/cell	130.9	105.1	90.8	65.9	52.2	41.0	24.9	19.2	15.5	12.7	11.14	9.02	7.52	4.07
1.75V/cell	142.0	113.6	96.8	68.1	53.9	42.7	25.8	19.5	15.8	13.0	11.43	9.17	7.59	4.10
1.70V/cell	152.6	120.4	101.2	70.6	55.9	44.0	26.7	20.0	16.2	13.3	11.65	9.29	7.66	4.18
1.65V/cell	163.6	127.2	107.0	74.2	57.1	45.3	27.4	20.8	16.7	13.7	11.89	9.43	7.81	4.22
1.60V/cell	174.6	134.4	112.8	77.5	58.9	46.5	28.1	21.4	17.2	14.1	12.12	9.51	7.89	4.24


DISCHARGE CHARACTERISTICS




TEMPERATURE EFFECTS IN RELATION TO BATTERY CAPACITY




SELF DISCHARGE CHARACTERISTICS



CHARGING CHARACTERISTICS (CYCLE USE)



CYCLE LIFE IN RELATION TO DEPTH OS DISCHARGE



No supplementary charge required (carry out supplementary charge before use if 100% capacity is required)

- В
- Supplementary charge required before use. Optional charging way as below: 1.Charged for above 3 days at limited current 0.25CA and constant voltage 2.25V/cell 2. Charged for above 20 hours at limited current 0.25CA and constant voltage 2.45V/cell 3. Charged for 8-10 hours at limited current 0.05CA

C Supplementary charge may often fail to recover the capacity. The battery should never be left standing till this is reached



Α